

## Steel Wire Cable Tray

# Steel Wire Cable Tray Standards

Marco Steel Wire Cable Tray conforms to the following standards:  
BSEN 61537:2007, IEC 61537

### Electro Zinc Coating (EZ) to standard BSEN12329:2000

The Marco Electro Zinc Plate finish is recommended for use in interior installations where the atmosphere is noncorrosive. Marco EZ coated steel wire cable tray is coated to a thickness of between 5-12 microns.

### Hot Dip Galvanising (HDG) to standard BSEN ISO1461:1999

The Marco Hot Dip Galvanised finish is recommended for exterior use and more aggressive atmospheres. Marco HDG tray is coated to a thickness of between 60-100 microns. White rust may appear on the surface of the tray wires without affecting its resistance to corrosion, this is due to the formation of zinc hydroxycarbonate.

### Pre Galvanised (PG) to standard BSEN 10244-2

The Marco Pre Galvanised finish is recommended for use in data centres and other interior applications. Marco PG steel wire cable tray is coated to a thickness of approximately 20 microns (135 gr/m<sup>2</sup> – class B).

### Electro-Zinc Plus to standard BSEN12329:2000

The Marco Electro-Zinc Plus finish is recommended for use in environments where Steel Wire Cable Tray is installed before the building is fully watertight and there is exposure to the elements for a short period of time. Marco Electro-Zinc Plus Steel Wire Cable Tray is coated to a thickness of over 20 microns.

### Powder Coated (PC) to standard BSEN 13438

The Marco Powder Coated finish is recommended for exterior and interior use in a range of atmospheric environments and is capable of withstanding a variety of corrosive conditions. It's installation is also suggested for use in data centres.

